

— ПОЛИЭТИЛЕН MF5000

Производитель: Uz-Kor Gas Chemical

Данный продукт применяется для производства моноволокна.

Properties			
Physical	Testing methods	Nominal values	
Density	ASTM D 1505	g/cm ³	0.951-0.956
Melt Flow Rate	ASTM D 1238	g/10min	0.8-1.1
Mechanical			
Tensile Strength at Yield (min.)	ASTM D 638	kg/cm ²	200
Tensile Strength at Break (min.)	ASTM D 638	kg/cm ²	220
Elongation at Break (min.)	ASTM D 638	%	500
Flexural Modulus (min.)	ASTM D790	kg/cm ²	9,000
Impact			
Izod Impact Strength (230C) (min.)	ASTM D256	kg cm/cm	10
Thermal			
Vicat Softening Point (min.)	ASTM D1525	°C	120
Heat distortion temperature (4.6 kg/cm ²) (min.)	ASTM D648	°C	50
Additional properties			
Rockwell Hardness (min.)	ASTM D785	R	45

ООО «Химическая индустрия»

www.himindustria.ru
 350002 г. Краснодар, ул. Северная, д. 490
 тел.: +7 861 298-06-97
 тел.: +7 861 298-15-97
 эл.почта: sales@himindustria.ru

